



We create chemistry

MasterSeal® M 800

(formerly known as Conipur M 800)

Spray applied elastomeric polyurethane waterproofing membrane

DESCRIPTION

MasterSeal M 800 is a solvent free highly elastic, two component waterproofing membrane. Due to its fast cure speed it can only be applied by special, two component spray equipment.

RECOMMENDED USES

MasterSeal M 800 is intended for use in general waterproofing applications such as car park decks, podium decks and cut and cover tunneling.

Using the appropriate primer, **MasterSeal M 800** can be applied to most substrates including concrete, galvanised steel, aluminium, UPVC, glass reinforced polyester etc.

FEATURES AND BENEFITS

- **Fast reacting spray application** – Complex details both horizontal and vertical easy to waterproof
- **Application to vertical surface without runs** – Installation to walls not problem
- **Monolithic** – No laps, welds or seams
- **Fully bonded** – Moves with the structure
- **High water vapour permeability** – Low risk of blistering in service
- **Crack bridging capability**- Can cope with cracks that occur after installation
- **Solvent and monomeric isocyanate free** – Increased safety for applicators
- **Unaffected by standing water or ground water** – Suitable for constant water contact
- **Thermoset** – Does not soften at elevated temperatures encountered on a roof
- **Remains elastic at low temperatures-Tg approx. -45°C** – Suitable for all Asia Pacific climates

PROPERTIES

Mixing ratio A:B by weight		100 : 73
by volume		100 : 70
Density @ 23°C	Part A	1.06 g/cm ³
	Part B	1.10 g/cm ³

Viscosity @ 23°C	Part A	>2400mPas
	Part B	>2500mPas
Ambient temperature range		5 °C to 40 °C
Substrate temperature range		5 °C to 40 °C
Relative humidity		max. 85 %

Technical data cured material
(sprayed film except where stated)

Shore A hardness	14 Days	>70
Tensile strength	ASTM D412	>8 MPa
Elongation	ASTM D412	>350%
Tear strength	ASTM D624	≥ 16 N/mm

The performance data is typical and based upon controlled laboratory conditions. Actual performance on the job site may vary from these values based on actual site conditions.

APPLICATION

Surface Preparation

The concrete substrates to be coated must be at least 14 days old, dry and load-bearing, free of laitance as well as substances which impair adhesion such as oil, grease, rubber skid marks, paint or other contaminants. Preparation of the substrate by grit or shot blasting, high-pressure water jetting, grinding or scarifying is necessary for plain concrete or when the primer has become soiled or when the re-coating interval has been exceeded. Prior to application of the primer the bond strength of the concrete substrate must be at least 1.2 MPa (check with an approved pull-off tester).

The substrate to be coated must be protected against rising damp by having a damp proof membrane installed if it is a slab in contact with the ground.

MasterSeal M 800 can only be applied by means of a suitable two component spray machine. For advice on machines, please contact your local BASF technical representative.



For Supplies please contact:
Bils Innovations (India) Pvt. Ltd.
Delhi, India
+91-11 42175807
+91 9582307311
Online Shop @ www.bilsinnovations.com

Ideas to Reality – Rendering Quality | Ecology | Safety



We create chemistry

MasterSeal® M 800

(formerly known as Conipur M 800)

MasterSeal M 800 when sprayed results in a uniform grey colour which gives the sprayer a visual control of the quality of the mixing as machine faults become immediately obvious. This can reduce costly clean up time and material wastage. Due to the fast reaction it is possible to rapidly build thicknesses from 1.0 to > 6 mm.

Surrounding areas should be protected from overspray by masking off with e.g. polyethylene sheet. or paper. Care should be taken to prevent spray mist being carried by wind by erecting suitable barriers. The temperature of the substrate should be min. 3°C above the dew point prior to application of the membrane.

Primer

Primer has to be cured to a 'tack-free' state prior to the application of MasterSeal M 800. Use the following guide to select the appropriate primer:

Substrate	Primer
Concrete	Mastertop P 660 MasterSeal P 2525
Other substrates	Contact your local BASF Construction Chemicals technical representative

Top Coats and Wear Coats

MasterSeal M 800 does not have sufficient UV and weather resistance to be used in exposed applications without protection. A number of top coats and wear coats are available including MasterSeal TC 269/268 which can be broadcast with dry silica sand to provide a hard wearing, non-slip surface.

Note: if rain falls or dew occurs on the surface of MasterSeal M 800 then the membrane must be dried and MasterSeal P 691 applied prior to the

application of any wear coat or two part top coat (even if the re-coat interval has not been exceeded). In the tropics any exposed MasterSeal M 800 must be treated as above if left overnight.

For more information about application, please obtain a copy of the BASF "Application Guide for MasterSeal Spray Membrane System" from your local representative.

ESTIMATING DATA

MasterSeal M 800 is normally applied at 1.8 – 2.4 kg/m². This corresponds to a thickness of approx. 1.8 – 2.4mm. Add for wastages depending on the area of application and site conditions.

PACKAGING

MasterSeal M 800 is supplied in 210kg drums – Part A and 220kg drums – Part B.

SHELF LIFE

Twelve months if stored in original containers under dry conditions at a temperature between 10-30° C. Do not store in direct sunlight for more than 3 days.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

ID#MasterSeal M800 IN v5.1016

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF Construction Chemicals publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

BASF India Limited
Construction Chemicals Division
Plot.No.12,TTC Area
Thane Belapur Road, Turbhe
Navi Mumbai - 400705, India
Tel: +91 22 67127600, Fax: +91 22 67917358
E-mail: construction-india@basf.com , www.master-builders-solutions.basf.in



For Supplies please contact:
Bils Innovations (India) Pvt. Ltd.
Delhi, India
+91-11 42175807
+91 9582307311
Online Shop @ www.bilsinnovations.com



Ideas to Reality – Rendering Quality | Ecology | Safety