



We create chemistry

MasterEmaco® S 348 (formerly known as Emaco S48CT)

Dual shrinkage compensated, trowelable fibre reinforced thixotropic repair mortar

DESCRIPTION

MasterEmaco S 348 trowelable mortar is a dual shrinkage compensated, thixotropic high strength formulation for structural concrete repairs.

MasterEmaco S 348 is suitable for placing in thicknesses of 12mm to 50 mm both vertically and overhead.

MasterEmaco S 348 provides a durable, strong structural repair fully compatible with host concrete.

RECOMMENDED USES

MasterEmaco S 348 is the ideal material for vertical or horizontal structural repairs where the thickness of repair is more than 10-12 mm and use of hand or machine applied structural repair systems is required. Typical applications are:

- Extensive repairs to beams, columns and other structural elements
- Repair of structural members subjected to repetitive loading

FEATURES AND BENEFITS

- **Dual shrinkage compensated** - volume stable in wet and hardened state reducing cracking tendency
- **One component, factory made only addition of water** - uniform predictable performance even in remote situations
- **No bonding agent required** - simple installation
- **Impermeable to aggressive elements** - long life repairs
- **Sprayable** - able to repair complex profiles easily with minimal rebound
- **Fast and easy placing** - reduced time for repairs

PROPERTIES

Appearance	Grey powder
Water powder ratio	0.16
Compressive strength (ASTM C109 7cm cube)	15 MPa 1 Day
	25 MPa 3 Days
	35 MPa 7 Days
	45 MPa 28 Days
Density	Approx. 2250kg/m ³
Mixing water per 25kg bag	Approx. 3.75– 4.25 litres
Application Temperature substrate	+5 to +40°C

material	+5 to +30°C
----------	-------------

APPLICATION

Surface preparation

All loose traces of concrete or mortar, dust, grease oil, etc. must be removed. Damaged or contaminated concrete shall be removed to obtain a keyed aggregate exposed surface. Non-impact/vibrating cleaning methods, e.g. grit or high pressure water blasting are recommended. Cut the edges of the repair vertically to a minimum depth of 5 mm. Clean all exposed reinforcement to a minimum grade of

SA 2 according to ISO 8501-1 / ISO 2944-4. Ensure back of rebar is also clean.

Where reinforcing bars are corroded, cut back the concrete to at least 20mm behind the reinforcing bars. Grit blast to remove corrosion products from around reinforcing bars and coat with **MasterEmaco P 130** to protect from corrosion. Replace the affected part of rebar if the diameter after grit blasting is found reduced by more than 20% of the original diameter on the advice of the structural engineer responsible for the works.

Mixing

Only full bags are mixed. Damaged or opened bags should not be used. Mix **MasterEmaco S 348** in a forced action pan mixer, or with a helical paddle attached to a low speed (300-600rpm) mixer for 3 minutes until a lump free, thixotropic consistency is achieved. Only use clean water. Mixing water needed: 3.75 to 4.25 litres per 25kg bag. Allow the mortar to rest for 2 - 3 minutes and then remix briefly before applying. If more than 30°C use chilled water as the mixing water.

Priming Concrete

No special primer is required. To obtain extra strong bonding, the damp substrate can be primed with a slurry brush coat of **MasterEmaco S 348** (2 parts powder to 1 part water).

Mortar application

The minimum temperatures must be maintained during application and for at least 24 hours thereafter for optimum curing of the product. The prepared substrate should be pre-soaked, preferably for 24 hours, but at least 2 hours before applying **MasterEmaco S 348**. The surface must be saturated surface dry, but without standing water. **MasterEmaco S 348** can be spray- or hand-applied. Apply mixed product directly to the prepared damp substrate, or wet on wet onto the



For Supplies please contact:
Bils Innovations (India) Pvt. Ltd.
Delhi, India
+91-11 42175807
+91 9582307311
Online Shop @ www.bilsinnovations.com



We create chemistry

MasterEmaco[®] S 348 (formerly known as Emaco S48CT)

primed surface. Spraying the material with the necessary pressure will ensure good adhesion of the material.

A thin scrape coat or contact layer before building up to the required thickness, wet on wet, will improve adhesion especially in case of hand application. Apply to the desired layer thickness of 12 to max 50 mm and level using a screeding bar, trowel or wooden board. Can be applied in thicker layers in smaller patches or where additional reinforcement is present. Smoothing with a trowel or finishing by float or sponge can be done as soon as the mortar has begun to stiffen.

Protective coatings

Subsequent coatings of **MasterProtect** anti carbonation barriers or silane impregnations should be applied as recommend on the individual datasheets.

CURING

MasterEmaco S 348 should be cured with **MasterKure181** or clear polythene sheeting

over wet hessian.

ESTIMATING DATA

Each bag of **MasterEmaco S 348** when mixed with 4.0L of water yields 12.8L.

PACKAGING

MasterEmaco S 348 is available in 25kg bags.

SHELF LIFE

MasterEmaco S 348 has a shelf life of 6 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

MasterEmaco S 348/01/0313

STATEMENT OF RESPONSIBILITY (Disclaimer)

The technical information and application advice given in this BASF Construction Chemicals publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

® = registered trademark of BASF group in many countries

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF Construction Chemicals either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

BASF India Limited
Construction Chemicals Division
Plot.No.12,TTC Area
Thane Belapur Road,Turbhe
Navi Mumbai - 400705,India
Tel: +91 22 67127600, Fax: +91 22 67917358
E-mail: construction-india@basf.com , www.master-builders-solutions.basf.in



For Supplies please contact:
Bils Innovations (India) Pvt. Ltd.
Delhi, India
+91-11 42175807
+91 9582307311
Online Shop @ www.bilsinnovations.com



Ideas to Reality – Rendering Quality | Ecology | Safety